


## Toplus Woodstain

TPWOOD  
1 & 5 Litre



### Description

**Toplus Woodstain** is a specially formulated Urethane Alkyd base high gloss enamel finish for protection of wooden surface. It has good water resistance, UV protection, anti fungus properties. It is fast drying and easily recoatable.

### Usage

Suitable for use in both interior and exterior where maintaining the texture of wood is desired.

### Composition

|              |   |   |
|--------------|---|---|
| Pigment      | : | Lightfast non-lead pigments and mineral extenders |
| Binder       | : | Urethane alkyd base                               |
| Volume Solid | : | 40 +/- 2%   |
| Diluent      | : | White Spirit                                      |

### Properties

|                      |   |  |
|----------------------|---|--|
| Finishing            | : | Gloss finish   |
| Colour               | : | Refer to color card.   |
| Theoretical Coverage | : | 10 - 12 m <sup>2</sup> /Litre (actual coverage dependent on substrate condition.)                |
| Drying Time          | : | * Touch dry – 30 minutes.<br>* Hard dry – 3 - 4 hour.<br>*Dependent on temperature and humidity. |
| Recoating Interval   | : | 3 to 4 hours.  |

### Application Method

|                        |   |   |
|------------------------|---|---|
| Brush                  | : | For normal use thinning is not usually necessary. |
| Roller                 | : | For normal use thinning is not usually necessary. |
| Conventional Air Spray | : | Thin with max 10% by volume with white spirit.    |

### Surface Preparation

| Surface                 | Preparation  |
|-------------------------|--|
| New Wood                | Surface generally must be clean, dry and free from oil, dirt, wax, grease or other contaminants. Recommend to test color on wood before decide the shade as final color shade depends on the type of wood applied. If gum is presence on surface, it must be clean by lacquer thinner. For recoating, the surface must be rub and clean. |
| Previously Painted Wood | Previously painted surface should be thoroughly rubbed down using suitable sandpaper and then dusted off.  |

## Painting Guide

| Surface | Sealer (1 coat) | Finish (1 - 3 coats) |
|---------|-----------------|----------------------|
| Wood    | -               | Toplus Woodstain     |

## Company Identification

Manufacturer : Smart Paints Manufacturing Sdn Bhd  
 No 9 & 11, Jalan Indah Gemilang 5, Taman Perindustrian Gemilang, 81800 Ulu Tiram, Johor, Malaysia  
 Telephone No. : +607-289 2855 Fax No. : +607-861 5055  
 Email : info@smart-paints.com